ANAEROBIC SEALANT

High resistance and/or permanent

Product informations

Anaerobic sealant for high strength metals (*SKU 50954*), to block and seal threaded joints, with high resistance to thermal shocks, vibrations, water, gases, oils and fuels, refrigeration fluids and various chemical agents.

Product features

- it can be used on all metals, both in free and forced couplings
- maintains sealing properties up to + 200°C

Permanent anaerobic sealant (*SKU 50957*) for metals with rapid polymerization and high mechanical resistance, to seal and block threaded joints and cylindrical couplings; with high resistance to thermal shocks, vibrations, chemical agents and aging.

NB. To seal PVC, PP or Nylon fittings, ***use only P.T.F.E. based sealant*** (*SKU 50950 / 50951*) by ***pre-treating*** the plastic threads with ***the activator*** (*SKU 50959*), ***screw and tighten within 1 minute*** (longer waiting times can break the sealant film that is already forming. ***Do not use the thread sealer*** on ABS and polycarbonate threads, for other types of materials ask in advance for our technical opinion.

TECNOGAS
I percorsi della tecnologia.

Via Marco Polo 33
35020 Albignasego
Padova – Italy

P.IVA: 03859580288
Tel: +39 049 8625910
Mail: info@tecnogas.net

Technical Features

SKU 50954	
MAX Ø FOR USE 2" - CLEARANCE 0,3 MM	
COLOR	GREEN
SURVEY	FLUORESCENT IN BLUE LIGHT
FLASH POINT	> + 100°C
MANIPOLATION	20 - 40 MINUTES
FUNCTIONAL HARDENING TIME	6 - 12 HOURS
FINAL HARDENING TIME	24 - 36 HOURS
TEMPERATURE RANGE	- 55°C ÷ + 200°C
DVGW GAS APPROVED FOR THREADED JOINTS ACCORDING TO EN 751-1	
WRAS APPROVED FOR CONTACT WITH DRINKING WATER	

SKU 50957	
MAX Ø FOR USE 1 1/2" - CLEARANCE 0,2 MM	
COLOR	GREEN
SURVEY	FLUORESCENT IN BLUE LIGHT
FLASH POINT	> + 100°C
MANIPOLATION	• BRASS (BARE) < 1 MINUTE • CHROMED AND NICKEL-PLATED BRASS 3 - 6 MINUTES • STEEL 2 - 5 MINUTES • ALUMINUM 6 - 18 MINUTES

TECNOGAS
I percorsi della tecnologia.
Via Marco Polo 33
35020 Albignasego
Padova – Italy
P.IVA: 03859580288
Tel: +39 049 8625910
Mail: info@tecnogas.net

SKU 50957	
FUNCTIONAL HARDENING TIME	1 - 3 HOURS
FINAL HARDENING TIME	2 - 4 HOURS
TEMPERATURE RANGE	- 55°C ÷ + 150°C
APPROVED FOR GAS (GAZ DE FRANCE)	

SKU	MODEL	PRICE
00000050954	HIGH RESISTANCE ANAEROBIC SEALANT 85-86 - 50 ML	€32.2 VAT EXCLUDED
00000050957	PERMANENT ANAEROBIC SEALANT 85-21 - 250 ML	€116.8 VAT EXCLUDED



TECNOGAS
I percorsi della tecnologia.
Via Marco Polo 33
35020 Albignasego
Padova – Italy
P.IVA: 03859580288
Tel: +39 049 8625910
Mail: info@tecnogas.net